



**International Timber Solutions**

ABN 97 124 632 444

## Radiata – AU - Green sawn IND & ROM Grade

- Species: pinus radiata - radiata pine – from Australia
- Sizes: 11mm – 150 mm thickness  
75mm – 240mm width  
Lengths 1.2m - 6.0m  
Specific sizes are possible by request ex Australia in 3.6m lengths (for example, 88x88, 93x93, 158x98, 98x78. This is defined as Run of Mill (ROM))
- Tolerances: green sawn cut +1/-0mm, upon arrival (shrinkage may be up to ~3%)  
typically flitch                    thickness +/- 3mm    widths +/- 3mm  
typically boards                 thickness +/- 1mm    widths +/- 2...3mm
- Finish: Sawn
- Wane: mostly allowable up to 1/3 face x 1/3 thickness x 1/3 length. Generally, only a small % of volume will have wane to the level of the allowable tolerance
- Pith: Allowable
- Blue Stain: Limited blue stain allowable.  
All other natural occurring defects including distortion are allowable
- Treatment: Anti-sap stain treated to protect from blue stain and mould for 3...6 months from date of treatment.  
Note: treatment protects the outer shell only (envelope treatment). Once the material is cut, ripped, split or otherwise opened up the exposed surface is prone to mould and blue stain. To prevent this, it is recommended to further process into pallet or otherwise ensure air movement around the timber within 24hrs of breaking the envelope.
- Log source: Flitches are typically cut from the centre of the log
- Typical applications Pallets, packaging, formwork, bins, crates, economical furniture components
- Note: As timber is a natural resource some variation is typical, it is however expected that a minimum of 95% of each pack will be within the tolerances specified herewith.



