



Radiata – NZ - KD Sawn COL & Better Grade

Species:	pinus radiata - radiata pine - from New Zealand
Sizes:	25 x 150/200 mm
Lengths	2.4 to 6.0m, heavy 3.6...5.4m
Tolerances:	thickness +/- 1.5 mm (mostly 24...24.5mm) widths +/- 3mm
Finish	sawn
Moisture:	KD target 10% -12% (Max 15%)
Stain:	Not permitted
Pith:	Not permitted
Resin:	Highly resinous material not permitted

Other defects: Each board will yield at least 60% recovery in clear shook of 200mm and longer in the full width of the board. Any other defects incl. dead knots and knot holes are generally allowed in this grade, although most knots are sound in the COL & Better.

Log source Typically cut from the transition zone between the clears and knotty of a pruned or part pruned log.

Face Boards are graded from the best face

Typical applications clear blocks for finger jointing, furniture, high end packaging

Note: As timber is a natural resource some variation is typical, it is however expected that a minimum of 95% of each pack will be within the tolerances specified herewith.

