



---

## **Radiata – NZ - KD Sawn IND Grade**

Species: pinus radiata - radiata pine – from New Zealand  
Thickness: 25, 38, 50, 75, 100 mm  
Width: 75, 100, 125, 150, 175, 200, 250, 300 mm  
Lengths: 1.2m – 6.0m  
Tolerances: thickness +/- 2mm widths +/- 3mm  
Finish Sawn  
Moisture: Up to 16%  
Wane: Will contain wane  
Pith: Mostly contains pith

All other natural occurring defects including distortion are allowable

Log source: Typically cut from the center of the log

Typical applications Pallets, packaging, formwork, bins, crates, economical furniture components

Note: As timber is a natural resource some variation is typical, it is however expected that a minimum of 95% of each pack will be within the tolerances specified herewith.



