



Radiata – NZ - KD Sawn PREM CUTTS Grade

Species:	pinus radiata - radiata pine - from New Zealand
Sizes:	25/32/38 x 150/200 mm Lengths 2.4 to 6.0m, heavy 4.2...5.4m
Tolerances:	thickness +/- 1mm widths +/- 3mm
Finish	sawn
Moisture:	KD target 10% -12% (Max 15%)
Wane:	Limited to <10mm on the occasional board.
Pith:	Not permitted
Spring:	Max. 45mm for a 6.0 metre length
Checking:	Two checks: max 1mm wide 100mm long.
Resin:	Pockets max 6mm wide x 50mm long. Highly resinous material not permitted
Stain:	Not permitted



Other defects:	May contain up to three major defects no more than 30mm. Defect combinations on the back face up to ½ the width of the board.
Log source	Typically cut from the transition zone between the clears and knotty of a pruned or part pruned log, so often one side is clear and the other could be No3 Cuts.
Face	Boards are graded from the best face
Grade reference	Mix of Clear 2 (one face/edge clear) to No3 Cuts (60% of its length in clear cuttings of 200mm+) 30-40% can be No3 Cuts. As a general rule, there won't be large numbers of 3m+ No1 Clears in this product as Clear 1 (Clear all sides) is graded out, however there are a lot of clears 2.4m and down. NZ Dressing grade standard min.

Typical applications furniture, boards, panelling, and high quality exterior use.

Note: As timber is a natural resource some variation is typical, it is however expected that a minimum of 95% of each pack will be within the tolerances specified herewith.

Best Face:



Worst Face:



Typical Defects:

