



Radiata – NZ – KD Sawn PREMIUM Grade

Species:	pinus radiata - radiata pine – from New Zealand
Sizes:	38x75/100/150/200 45x75/100/150/200
Lengths	2.4 to 6.0, heavy 4.2...5.4
Tolerances:	thickness +/- 1mm widths +/- 3mm
Finish	sawn
Moisture:	KD target 10% -12% (Max 15%)
Wane:	Limited to <10mm on the occasional board.
Pith:	Not permitted
Spring:	Max. 45mm for a 6.0 metre length
Checking:	Two checks: max 1mm wide 100mm long.
Resin:	Pockets max 6mm wide x 50mm long. Highly resinous material not permitted
Stain:	Not permitted

Log source	Typically cut from clear sap area of a pruned or part pruned log
Face	Boards are graded from the best face
Grade reference	~20-25% Clears 1 ~20-30% Clear 2 (with some Clear 3) ~40-60% Cuts 1(60% recovery of 1.8m and longer 1) and Cuts 2 (70% recovery of 600mm or longer clear) Wider widths will yield the lower percentage of higher grade, and narrower widths will yield a higher percentage of higher grade.

Typical applications furniture, boards, panelling, and high quality exterior use.

Note: As timber is a natural resource some variation is typical, it is however expected that a minimum of 95% of each pack will be within the tolerances specified herewith.



Worst face of several layers:

